稳定同位素 ^{13}C 标记富勒醇结构的探索

李红亮^{1,2}, 汪称龙², 杨胜韬^{1,2*}, 常雪灵^{2*}

1. 西南民族大学化学与环境保护工程学院, 成都 610041;

2. 中国科学院高能物理研究所, 中国科学院纳米生物效应与安全性重点实验室, 北京 100049

* 联系人, E-mail: yangst@pku.edu.cn; changxl@ihep.ac.cn

2017-03-03 收稿, 2017-03-24 修回, 2017-03-28 接受, 2017-05-11 网络版发表

国家自然科学基金(11475194)、北京市自然科学基金(2152038)和国家重点研发计划(2016YFA0201600)资助

摘要 富勒醇是具有良好生物相容性的富勒烯衍生物, 因其具有低毒、抗肿瘤活性、抗病毒活性、抗氧化活性及光敏性等优势被广泛研究, 发现其碳笼表面修饰的含氧基团决定其在生物医学应用中的生物效应。然而, 富勒醇的结构比较复杂, 尚未能精确描述。本文以稳定同位素 ^{13}C 标记技术, 通过富勒烯(C_{60})胺碱催化-氧化合成 ^{13}C 骨架标记的富勒醇, 结合质谱、红外光谱、X光电子能谱(XPS)及 ^{13}C 核磁共振谱(^{13}C NMR)对其测试表征, 探索富勒醇的精确结构。结果发现, 稳定同位素 ^{13}C 碳笼骨架标记极大地提高了 ^{13}C NMR 信号强度, 富勒醇分子结构的 ^{13}C NMR 谱中清晰呈现出乙烯基醚碳、未反应烯碳、羟基化碳的信号, 即不仅存在未氧化的碳和单氧化的碳, 还存在高氧化的碳, 与 XPS 测试结果吻合。富勒醇的碳笼表面修饰基团以羟基、半缩醛/酮、环氧以及羰基等结构存在。富勒醇复杂表面基团修饰结构的确定对其未来广泛的生物医学应用具有重要意义。

关键词 富勒醇, 稳定同位素 ^{13}C 标记, ^{13}C 核磁共振谱, 结构分析

自富勒烯 C_{60} 首次被发现以及通过电弧放电宏量合成^[1,2], 三十多年来富勒烯 C_{60} 已引起全世界科学工作者的广泛关注, 并掀起了持续的研究热潮, 对其结构、性质和应用方面的研究也取得了快速而深入的发展。由于富勒烯极难溶于水(0.1 ng/mL)^[3], 极大限制了其在水溶性环境生物体系中的应用, 且具有一定的生物毒性, 使其研究和应用都受到了较大地限制^[4]。富勒醇作为一种富勒烯羟基化修饰的衍生物, 不仅具有良好的水溶性和低毒性, 而且具有抗肿瘤、抗病毒、抗菌、抗氧化及光敏性的特点^[5-7], 在材料研究、生物医药等领域具有重要意义^[8,9], 因此富勒醇纳米材料在近年来受到了广泛的关注和研究。

然而, 富勒醇的结构非常复杂, 人们对其结构的描述极为模糊, 尚未获得精准的富勒醇结构信息。比较常见富勒醇制备方法有 $\text{HNO}_3/\text{H}_2\text{SO}_4$ 混酸合成

法^[10]、 RCO_2NO_2 亲电加成法^[11]、过量固态 KOH 真空加热氧化法^[12]、以及沸腾富勒烯甲苯液溶钾片回流法^[13]等, 但这些方法呈现出反应条件复杂、反应时间过长、操作不易控制等不利因素。最简单常用的方法当属碱催化-氧化合成法^[14,15], 其主要是利用胺作为相转移催化剂, 在碱性条件下以双氧水为氧化剂, 快速而高产率地获得富勒醇。该方法不仅反应速率高, 而且反应温和, 易于操作。然而, 无论采用哪种方法获得的富勒醇的精确结构仍然需要进一步研究探索, 如碳笼表面修饰羟基个数, 表面含氧修饰基团的可能形式, 以及表面基团修饰的位置等。研究发现, 富勒醇碳笼表面羟基数目及其可能的存在形式将直接决定其生物学行为的变化^[16,17]。在纳米尺度上, 化学结构上一个微妙的变化足以显著改变其生物学性质, 从而最终影响其生物相容性和应用^[18]。因此对富勒

引用格式: 李红亮, 汪称龙, 杨胜韬, 等. 稳定同位素 ^{13}C 标记富勒醇结构的探索. 科学通报, 2017, 62: 1714–1720

Li H L, Wang C L, Yang S T, et al. Structural investigation of the stable isotope ^{13}C labeled fulleranol (in Chinese). Chin Sci Bull, 2017, 62: 1714–1720, doi: 10.1360/N972017-00178

醇结构的探索与研究,显得尤为重要。

本文利用稳定同位素 ^{13}C 碳笼骨架直接标记技术,保持富勒烯纳米材料本征结构和性质的同时提高富勒醇中 $^{13}\text{C}/^{12}\text{C}$ 的丰度,从而增加 ^{13}C 核磁共振信号的强度^[19],有利于探索和研究富勒醇的精确结构。以实验室自制的稳定同位素 ^{13}C 骨架标记的富勒烯 C_{60} 为原料^[20],采用较为简单的四丁基氢氧化铵(TBAH)胺碱催化-氧化合成法,变换氢氧化钠(NaOH)的碱液浓度,制备了一系列不同羟基化程度的稳定同位素 ^{13}C 标记的多羟基富勒烯-富勒醇,结合飞行时间质谱、红外光谱、X光电子能谱(XPS)、 ^1H 核磁共振(^1H NMR)及 ^{13}C 核磁共振谱(^{13}C NMR)等谱学信息,从分子水平上对合成的富勒醇样品进行结构分析,探究富勒醇样品碳笼表面的氧化程度及可能的存在形式,确定富勒醇的精确结构。这将为安全、无损的碳纳米材料体内定量检测以及富勒醇的构效关系研究奠定重要的物质基础。

1 材料和方法

(i) 试剂和仪器。氘代二甲基亚砜(DMSO, 0.6 mL)和Sephadex G-25葡聚糖凝胶(25 g)均购自Sigma公司;四丁基氢氧化铵(TBAH, 50%, 分析纯, 国药集团化学试剂有限公司)、双氧水(30%, 分析纯)、氢氧化钠(分析纯)、甲醇(分析纯)和甲苯(分析纯)均购自北京化学试剂公司;超纯水和稳定同位素 ^{13}C 标记富勒烯 C_{60} (纯度 $\geq 99.5\%$)^[20]为实验室自制。Autoflex激光基质辅助飞行时间质谱仪(Autoflex, 德国Bruker公司)、显微红外光谱仪(Nicolet iNIO MX, 美国Thermo公司)、X光电子能谱仪(ESCA Lab 220I-XL型, 英国VG公司)、核磁共振谱仪(AvanceDRX 500 MHz, 瑞士Bruker公司)和冷冻干燥仪(FD-1, 中国北京德天佑科技发展有限公司)。

(ii) 富勒醇的制备。在100 mL圆底烧瓶中分别加入4个不同浓度(0.5, 1.0, 1.5, 2.0 g/mL, 分别标号为A, B, C, D)的NaOH溶液10 mL, 不断搅拌, 缓慢加入0.25 mL TBAH(50%)溶液, 再滴加1.0 mg/mL的 $^{13}\text{C}-\text{C}_{60}$ 甲苯液20 mL, 20 min匀速滴完;随后滴加 H_2O_2 溶液0.5 mL, 避光持续搅拌反应4 h。出现明显分层现象, 上层为无色有机相, 下层为棕黑色水相沉淀。以分液漏斗将上述有机相与水相分离, 水相再过滤, 滤除水不溶性颗粒, 保留滤液, 加入甲醇沉淀, 离心去除上清甲醇溶液, 获得棕黑色沉淀。将棕黑色

沉淀继续水溶, 甲醇沉淀, 离心除上清甲醇溶液, 此过程反复4~5次, 直至上清甲醇溶液 $\text{pH} \leq 8$, 以洗去残留NaOH及TBAH。最后沉淀经50℃减压真空干燥, 获得棕黑色固体^[21~24], 再经凝胶层析柱进一步纯化, 去除 Na^+ 和相转移剂。取棕黑色固体, 溶于超纯水中, 过凝胶柱(Sephadex G-25, 1 cm $\times$ 30 cm), 流速1.0~1.5 mL/min, 收集流出液棕黑色组分, 旋转蒸发浓缩后冷冻干燥, 得富勒醇固体粉末。

2 结果与讨论

2.1 飞行时间质谱对富勒醇样品的结构分析

^{13}C 标记富勒醇样品水溶液滴在质谱靶板上, 自然挥干, 进行飞行时间质谱检测。如图1所示, 富勒醇样品的质谱图不仅呈现 ^{13}C 标记富勒烯 C_{60} 正态分布的同位素分布图, 而且还有拖尾峰出现。与文献[20,24,25]报道一致, ^{13}C 标记后的 C_{60} 同位素分布峰形从陡峭分布变成高斯分布, m/z 最强信号峰随之迁移增大, m/z 为726的是碳笼结构的最强信号峰, 这些表明在上述富勒醇制备过程中, C_{60} 的笼形结构保持完整。富勒醇样品质谱图中相对微弱的拖尾峰, m/z 为743的是其最强信号峰, 也呈高斯分布(图1), 为 ^{13}C 标记碳笼的氧化峰, 这与 ^{13}C 标记 C_{60} 的质谱图不同, 后者的质谱图中不存在这种拖尾氧化峰。在质谱测试时, 富勒醇表面羟基修饰基团易于被强烈的激光打碎, 从而在质谱图中呈现出富勒烯 C_{60} 表面修饰后的拖尾氧化峰。因此, 基于质谱图分析, 实验成功获得了碳笼骨架 ^{13}C 标记的富勒醇, 这种胺碱催化-氧化合成法制备富勒醇的过程, 不会破坏富勒烯碳笼基本结构的稳定性。

图1 ^{13}C 标记富勒醇的飞行时间质谱图
Figure 1 Time-of-flight mass spectrum of ^{13}C labeled fullerol

2.2 红外吸收光谱对富勒醇样品的结构分析

取少量 ^{13}C 标记富勒醇样品粉末,置于氟化钡载玻片上,进行显微红外观察,如图2所示.富勒醇样品红外谱图中呈现4个明显的特征峰,即 3340 cm^{-1} 处强而宽的羟基特征吸收峰, 1576 cm^{-1} 处 $\text{C}=\text{C}$ 双键吸收峰, 1372 cm^{-1} 处羟基($\text{O}-\text{H}$)的面内弯曲振动峰和 1074 cm^{-1} 处 $\text{C}-\text{O}$ 单键伸缩振动峰.表明样品分子中碳笼表面被氧化,含有大量羟基,并且其分子间或内部产生了较强的氢键相互作用.

2.3 XPS对富勒醇样品的结构分析

采用压片法制样,取少量富勒醇样品粉末,均匀涂覆在 $1\text{ cm}\times 1\text{ cm}$ 的铝箔粗糙面上,盖上相同大小的铝箔(滑面朝下),然后在压片机 10 MPa 条件下,压片 10 s ,用镊子小心撕开盖上的铝箔,取出进行XPS检测.通过XPS对4个不同碱性浓度下获得的富勒醇样品分子结构进行仔细分析,样品结合能谱中的碳峰进行分峰拟合,分析不同氧化形态的碳,根据下式^[22,23]计算不同形态碳原子的比例,推测其可能的分子结构式,分析富勒烯碳笼外羟基化修饰可能带来的复杂基团结构形式.

$$n_{\text{OH}} = \frac{\text{Area}_{\text{oxidized}}}{\text{Area}_{\text{oxidized}} + \text{Area}_{\text{non-oxidized}}} \times 60.$$

图3显示氢氧化钠浓度为 1.0 g/mL 时,富勒醇样品中 $\text{C } 1\text{s}$ 的XPS拟合分峰图,峰号1,2及3分别表示未氧化的碳、单氧化的碳及高氧化的碳.说明产物中可能存在 $-\text{OH}$,环氧和 $\text{C}=\text{O}$ 双键含氧等基团.从图中各峰的相对面积大小可知,未被氧化碳的峰面积最大,说

图2 ^{13}C 标记富勒醇的红外吸收光谱图

Figure 2 Infrared absorption spectrum of ^{13}C labeled fullerol

图3 富勒醇样品的 $\text{C } 1\text{s}$ XPS拟合图谱. 1, 2及3信号分别表示未氧化的碳、单氧化碳及高氧化形态的碳

Figure 3 $\text{C } 1\text{s}$ XPS spectrum of fullerol sample. 1, 2 and 3 signals were assigned to the pristine carbon, single oxidized carbon and highly oxidized carbon, respectively

明碳笼上的碳多数未被氧化;单氧化碳峰面积大于高氧化碳峰面积,说明产物中与羟基相连的碳数目多于与碳氧双键相连的碳,即羟基氧的数目大于高氧化碳相连的氧的数目.碳氧双键可能是以半缩醛/酮及羧酸酯的形式存在.

经过进一步的XPS测试数据分析,发现4种富勒醇样品的拟合峰结合能变化不显著(表1), $284.56\sim 284.86\text{ eV}$ (碳原子百分比为 $57.00\%\sim 63.90\%$)为未氧化的碳; $286.07\sim 286.38\text{ eV}$ (碳原子百分比为 $10.78\%\sim 17.25\%$)为单氧化的碳; $288.57\sim 288.82\text{ eV}$ (碳原子百分比为 $5.69\%\sim 6.72\%$)为高氧化的碳.富勒醇样品(A~D)中相同形态的碳原子,其结合能有轻微变化,这说明在不同碱性浓度下,合成的富勒醇中碳笼表面氧化程度略有不同会引起富勒烯碳笼电子结构的微弱变化,这与文献[6,7]报道相符.

根据XPS测试,富勒醇样品(A~D)中各元素占比为: C, $76\%\sim 82\%$; O, $14\%\sim 18\%$; Na, $0.6\%\sim 4\%$.根据上述公式,计算推测富勒醇样品(A~D)可能的分子结构式见表2.不同碱浓度条件下合成的富勒醇样品中均有少量 Na^+ , 4~6个碳氧双键和8~14个羟基^[24].检测出的 Na^+ 可能来自于纯化过程中未完全去除的氢氧化钠,与阴离子形式的富勒醇共存于溶液中,故其可能的结构通式为 $\text{Na}_n^+[\text{C}_{60}\text{O}_x(\text{OH})_y]^{n-}$ ^[22].从表2可以看出,从样品A到C,随其合成所用的碱浓度逐渐增大,富勒醇含氧量越高,碳笼氧化程度越高,总氧数目达17~19,羟基数目为12~14;当样品D中碱浓度达到饱和(2.0 g/mL)时,抑制了碳笼的氧化程度,使富勒

表 1 4 个富勒醇样品XPS各峰的结合能和峰面积百分比

Table 1 Binding energy and area percentage of each peak in the XPS spectra of four fulleranol samples

	样品编号	C-C	C-O	C=O	Na 1s
结合能(eV)	A	284.80	286.22	288.79	1071.44
	B	284.56	286.07	288.57	1071.15
	C	284.86	286.38	288.73	1071.50
	D	284.82	286.36	288.82	1071.24
峰面积百分比(%)	A	57.97	17.25	6.24	0.67
	B	57.00	17.01	6.28	1.27
	C	53.32	16.73	6.72	3.81
	D	63.90	10.78	5.69	0.94

表 2 4 个富勒醇样品的分子结构式

Table 2 Molecular structural formulas of four fulleranol samples

样品编号	样品分子式	总氧数
A	$\text{Na}_{1.38}^+[\text{C}_{60}\text{O}_{4.59}(\text{OH})_{12.70}]^{1.38-}$	17.29
B	$\text{Na}_{0.95}^+[\text{C}_{60}\text{O}_{4.69}(\text{OH})_{12.72}]^{0.95-}$	17.41
C	$\text{Na}_{2.97}^+[\text{C}_{60}\text{O}_{5.25}(\text{OH})_{13.07}]^{2.97-}$	18.32
D	$\text{Na}_{1.20}^+[\text{C}_{60}\text{O}_{4.25}(\text{OH})_{8.04}]^{1.20-}$	12.29

醇中总氧数目下降, 羟基数目也下降. 当样品C中碱浓度达到饱和(1.5 g/mL)时, Na^+ 的数目最多, 趋于3. 因此, 在合成富勒醇的TBAH胺碱催化-氧化合成法中, 选择合适的碱浓度非常重要, 碱浓度的高低对富勒醇样品中羟基数和碳原子的存在形式都具有一定影响. 碳氧双键可能以半缩醛/酮及羧酸酯的形式存在^[26].

2.4 ^1H NMR谱对富勒醇样品的结构分析

为进一步阐明富勒醇的分子结构, 对富勒醇样品进行 ^1H NMR分析. 取2.0 mg富勒醇样品B, 溶于0.6 mL氘代二甲基亚砜(DMSO)溶剂, 转移至核磁管中, 具塞密封, 进行 ^1H NMR检测. 如图4所示, 富勒醇样品的氢质子化学位移 δ 在1.23, 2.50和3.34处, 其中, δ 3.34的信号强度最强, 为氘代试剂中含有微量水所产生水峰; δ 2.50处的次强峰为含有氢质子的DMSO溶剂峰; δ 1.23处的信号强度相对较弱, 为羟基特征峰, 与文献[27~29]报道相符. Andreeva等人^[27]认为富勒醇中羟基峰的氢质子化学位移在0.8和1.2处; 杨百霞^[28]与张晓敏等人^[29]对富勒醇的研究也认为1.24为羟基中的氢质子化学位移. 说明实验合成中已将羟基基团引入到 C_{60} 的碳笼上, 在核磁测试时,

图 4 ^{13}C 标记富勒醇的 ^1H NMR谱图

Figure 4 ^1H NMR spectrum of ^{13}C labeled fulleranol

产生去屏蔽作用, 使共振信号向高场移动, 化学位移变小. 此外, 碳笼外表面氧化基团存在的形式和数目不同, 与氘代DMSO溶剂或杂质水将发生不同程度的缔合或氢氧交换, 也将会影响富勒醇样品中氢质子的信号强弱.

2.5 ^{13}C NMR谱对富勒醇样品的结构分析

^{13}C NMR能够表征样品结构中不同类型碳以及处于不同化学环境中的碳的情况. 通过比较 ^{13}C 标记富勒醇样品与未标记富勒醇样品的碳的化学位移以及信号强度特点, 可以进一步确定其结构. 在室温条件下, ^{13}C NMR测试 ^{13}C 标记和未标记的富勒醇的氘代水饱和溶液. 如图5所示, ^{13}C 标记富勒醇样品的 ^{13}C NMR信号强度显著大于未标记富勒醇, 即引入 ^{13}C 使富勒醇样品 ^{13}C NMR信号增强. 原因在于 ^{13}C 标记提高了 ^{13}C 的相对丰度, 使 ^{13}C 的 γ_{C} 增大, 其检测灵敏度提高, 信号随之增强. 由图5可知两个样品均在 δ 175,

图5 富勒醇样品的 ^{13}C NMR谱图. (a) 富勒醇; (b) ^{13}C 标记富勒醇

Figure 5 ^{13}C NMR spectra of fullereneol samples. (a) Fullereneol; (b) ^{13}C labeled fullereneol

137, 75~80这3个板块出峰, 结合文献[7,26,28]报道分析, 这3个板块分别代表乙烯基醚碳($\text{C}=\text{C}-\text{O}$)、未反应的烯碳($\text{C}=\text{C}$)、羟基化的碳($\text{C}-\text{OH}$). δ 160处为羧基($\text{O}=\text{C}-\text{OH}$)结构中的碳; δ 100处为半缩醛($\text{RO}-\text{RCH}-\text{OH}$)或半缩酮($\text{RO}-\text{R}_1\text{CR}_2-\text{OH}$)结构中的碳; δ 54处为环氧结构中的碳. ^{13}C NMR谱图分析充分说明了富勒醇分子结构的复杂和多样性, 富勒醇样品碳笼表面存在多种结构的含氧基团, 不仅存在羟基, 也存在半缩醛/酮、环氧以及羰基结构. 与XPS所推测的结果相互印证, 证明了富勒醇的碳笼上不仅引入羟基, 同时存在羧酸酯($\text{O}=\text{C}-\text{OH}$)或羰基($\text{C}=\text{O}$)、半缩醛($\text{RO}-\text{RCH}-\text{OH}$)、半缩酮($\text{RO}-\text{R}_1\text{CR}_2-\text{OH}$)等形式的碳, 还可能有乙烯基醚碳($\text{C}=\text{C}-\text{O}$)等.

3 结论

本文以 ^{13}C 骨架标记的富勒烯 C_{60} 为原料, 通过胺碱催化-氧化合成法, 制备了一系列不同羟基化修饰

的稳定同位素 ^{13}C 标记的多羟基富勒烯——富勒醇, 并采用飞行时间质谱、红外光谱、XPS, ^1H NMR及 ^{13}C NMR对富勒醇的分子结构进行探索. 在合成过程中, ^{13}C 标记技术的引入不仅证明了富勒醇胺碱催化-氧化合成过程中碳笼结构的完整性, 而且显著提高了富勒醇样品的 ^{13}C NMR检测的灵敏度, 结合其XPS数据分析, 说明富勒醇的合成过程中碳笼发生了不同程度的氧化反应. 产物结构中存在未反应的碳、单氧化态的碳合高氧化的碳, 碳笼外不仅有独立的羟基基团, 而且含有半缩醛/酮、环氧、羧酸酯、羰基等基团, 在酸碱条件下, 很可能易于发生互变异构和重排反应. 富勒醇分子较为确切的结构式为 $\text{Na}^+_n[\text{C}_{60}\text{O}_x(\text{OH})_y]^{n-}$, 富勒醇分子结构的复杂性需要在实际应用中具体的分析和研究. 这种以稳定同位素标记确证富勒醇分子复杂结构的探究将为其生物体内定量、生物效应及其构效关系等研究奠定重要的基础, 有助于富勒醇药物的进一步开发和应用.

参考文献

- Kroto H W, Heath J R, O'Brien S C, et al. C_{60} : Buckminsterfullerene. *Nature*, 1985, 6042: 162–163
- Kratschmer W, Lamb L D, Fostiropoulos K, et al. Solid C_{60} : A new form of carbon. *Nature*, 1990, 6291: 354–358
- Kraszewski S, Tarek M, Ramseyer C. Uptake and translocation mechanisms of cationic amino derivatives functionalized on pristine C_{60} by lipid membranes: A molecular dynamics simulation study. *ACS Nano*, 2011, 11: 8571–8578
- Sijbesma R, Srdanov G, Wudl F, et al. Synthesis of a fullerene derivative for the inhibition of HIV enzymes. *J Am Chem Soc*, 1993, 115: 6510–6512
- Chiang L Y, Bhonsle J B, Wang L, et al. Efficient one-flask synthesis of water-soluble [60]fullerenols. *Tetrahedron*, 1996, 52: 4963–4972
- Chiang L Y, Swirczewski J W, Hsu C S, et al. Multi-hydroxy additions onto C_{60} fullerene molecules. *J Chem Soc Chem Commun*, 1992, 24: 1791–1793
- Chiang L Y, Upasani R B, Swirczewski J W, et al. Evidence of hemiketals incorporated in the structure of fullerols derived from aqueous acid chemistry. *J Am Chem Soc*, 1993, 115: 5453–5457

- 8 Chiang L Y, Lu F J, Lin J T. Free radical scavenging activity of water-soluble fullerenols. *J Chem Soc Chem Commun*, 1995, 12: 1283–1284
- 9 Zhu Y S, Sun D Y, Liu G Z, et al. An ESR study on OH-radical scavenging activity of water-soluble fullerenols (in Chinese). *Chem J Chin Univ*, 1996, 7: 1127–1129 [祝严师, 孙大勇, 刘桂珍, 等. 富勒醇清除 OH 自由基的 ESR 研究. 高等学校化学学报, 1996, 7: 1127–1129]
- 10 Chiang L Y, Wang L Y, Swirczewski J W, et al. Efficient synthesis of polyhydroxylated fullerene derivatives via hydrolysis of polycyclisulfated precursors. *J Org Chem*, 1994, 14: 3960–3968
- 11 Chiang L Y, Upasani R B, Swirczewski J W. Versatile nitronium chemistry for C₆₀ fullerene functionalization. *J Am Chem Soc*, 1992, 26: 10154–10157
- 12 Naim A, Shevlin P B. Reversible addition of hydroxide to the fullerenes. *Tetrahedron Lett*, 1992, 47: 7097–7100
- 13 Sun D Y, Liu Z Y, Guo X H, et al. Convenient preparation and properties of C₆₀(OH)_x (in Chinese). *Chem J Chin Univ*, 1996, 1: 19–20 [孙大勇, 刘子阳, 郭兴华, 等. C₆₀(OH)_x 的简便合成及性质. 高等学校化学学报, 1996, 1: 19–20]
- 14 Li T B, Li X H, Huang K X, et al. Synthesis and characterization of hydroxylated fullerene epoxide—An intermediate for forming fullerol. *J Central South Univ Technol*, 1999, 1: 35–36
- 15 Li T B, Huang K X, Li X H, et al. Studies on the rapid preparation of fullerols and its formation mechanism (in Chinese). *Chem J Chin Univ*, 1998, 6: 858–860 [李添宝, 黄克雄, 李新海, 等. C₆₀(OH)_n 的快速制备及其机理研究. 高等学校化学学报, 1998, 6: 858–860]
- 16 Bogdanović G, Kojić V, Đorđević A, et al. Modulating activity of fullerol C₆₀(OH)₂₂ on doxorubicin-induced cytotoxicity. *Toxicol In Vitro*, 2004, 5: 629–637
- 17 Li J, Zhang M, Sun B, et al. Separation and purification of fullerlenols for improved biocompatibility. *Carbon*, 2012, 2: 460–469
- 18 Nel A E, Madler L, Velegol D, et al. Understanding biophysicochemical interactions at the nano-bio interface. *Nat Mater*, 2009, 7: 543–547
- 19 Cai W, Piner R D, Stadermann F J, et al. Synthesis and solid-state NMR structural characterization of ¹³C-labeled graphite oxide. *Science*, 2008, 5897: 1815–1817
- 20 Ruan L F, Chang X L, Sun B Y, et al. Preparation and spectra of ¹³C-enriched fullerene (in Chinese). *Chin Sci Bull (Chin Ver)*, 2014, 59: 905–912 [阮龙飞, 常雪灵, 孙宝云, 等. 稳定同位素 ¹³C 标记 C₆₀ 的制备及光谱性质. 科学通报, 2014, 59: 905–912]
- 21 Xing G M, Zhang J, Zhao Y L, et al. Influences of structural properties on stability of fullerlenols. *J Phys Chem B*, 2004, 31: 11473–11479
- 22 Yang S T, Wang H F, Guo L, et al. Interaction of fullerlenol with lysozyme investigated by experimental and computational approaches. *Nanotechnology*, 2008, 39: 395101
- 23 Husebo L O, Sitharaman B, Furukawa K, et al. Fullerenols revisited as stable radical anions. *J Am Chem Soc*, 2004, 38: 12055–12064
- 24 Ruan L F. Preparation and property analysis of stable isotope ¹³C labeling of fullerenes and their derivatives (in Chinese). Master Dissertation. Wuhan: Hubei University of Traditional Chinese Medicine, 2014 [阮龙飞. 稳定同位素 ¹³C 标记富勒烯及其衍生物的制备和性质分析. 硕士学位论文. 武汉: 湖北中医药大学, 2014]
- 25 Wang C L, Ruan L F, Chang X L, et al. The isotopic effects of ¹³C-labeled large carbon cage (C₇₀) fullerenes and their formation process. *RSC Adv*, 2015, 94: 76949–76956
- 26 Wang Z Z, Chang X L, Lu Z H, et al. A precision structural model for fullerlenols. *Chem Sci*, 2014, 8: 2940–2948
- 27 Andreeva D V, Ratnikova O V, Melenevskaya E Y, et al. The regioselectivity of fullerlenols C₆₀(OH)_x determined by high-resolution solid-state ¹³C and ¹H NMR analysis. *Int J Polym Anal Charact*, 2007, 2: 105–113
- 28 Yang B X. The development of an novel nucleus targeting nanomaterial C₆₀(OH)₂₄-NLC-E for the radiation protection (in Chinese). Master Dissertation. Suzhou: Soochow University, 2012 [杨百霞. 细胞核靶向富勒醇固体脂质纳米粒的辐射防护作用. 硕士学位论文. 苏州: 苏州大学, 2012]
- 29 Zhang X M, Deng B, Li J Y, et al. Preparation of fullerlenol from fullerene by use of UV light oxidation (in Chinese). *J Radiat Res Radiat Process*, 2010, 1: 1–4 [张晓敏, 邓波, 李景烨, 等. 紫外光氧化法制备水溶性富勒醇. 辐射研究与辐射工艺学报, 2010, 1: 1–4]

Summary for “稳定同位素 ^{13}C 标记富勒醇结构的探索”

Structural investigation of the stable isotope ^{13}C labeled fullereneol

LI HongLiang^{1,2}, WANG ChengLong², YANG ShengTao^{1,2*} & CHANG XueLing^{2*}¹ College of Chemistry and Environment Protection Engineering, Southwest Minzu University, Chengdu 610041, China;² CAS Key Laboratory for Biomedical Effects of Nanomaterials and Nanosafety, Institute of High Energy Physics, Chinese Academy of Sciences, Beijing 100049, China

* Corresponding authors, E-mail: yangst@pku.edu.cn; changxl@ihep.ac.cn

Fullerenes are novel carbon nanomaterials that hold great promise in diverse areas, but the limited solubility make them hardly dispersible in aqueous environment and the applications in hydrophilic systems are restricted, in particular for biomedical areas. Currently, chemical functionalization is the main approach to increase the hydrophilicity of fullerenes, where the soluble fullerene derivatives show lower toxicity and interesting bio-effects. Among these fullerene derivatives, hydroxylated fullerene (fullereneol) has good biocompatibility, antitumor activity, antiviral activity, antioxidation activity and photosensitive activity, thus is widely studied and applied. The structure and functionalization of fullereneol determine the bio-effects in biomedical applications. However, the structure of fullereneol is very complicated and the precise structure of fullereneol has not been achieved yet, such as the hydroxyl group number, the position of functional groups and the chemical forms of surface groups. Herein, we adopted ^{13}C stable isotope labeling to investigate the chemical structure of fullereneol. ^{13}C -skeleton labeled fullerene C_{60} was prepared by arc discharge method. Then, ^{13}C - C_{60} was hydroxylated by tetrabutylammonium hydroxide (TBAH) amine alkali catalysis-oxidation to obtain ^{13}C -fullereneol. The ^{13}C -fullereneol was characterized by TOF-MS, IR, X-ray photoelectron spectroscopy (XPS), NMR to analyze the structure of fullereneol. The results indicated that ^{13}C atoms were labeled on the skeleton of fullerene cage. Hydroxylation did not break the carbon cage, which was reflected by the strong C_{60} peak in the TOF-MS spectrum. The Poisson distribution of mass spectra indicated the isotopic effects and the skeleton labeling by ^{13}C . Based on the TOF-MS, there were about five ^{13}C atoms on each fullerene cage. The higher mass signals were assigned to the oxidized fullerene cage and the lack of very large mass signal suggested the detachment of functional groups during the laser irradiation. The oxygen containing groups were confirmed by IR spectrum. A 3340, 1372 and 1074 cm^{-1} peaks were attributed to be C–O/C–OH groups. XPS analyses indicated the chemical components of fullereneol as C 76%–82%, O 14%–18% and Na 0.6%–4%. The C 1s XPS spectra were divided into three major components, namely 284.56–284.86 eV for pristine carbon, 286.07–286.38 eV for C–O and 288.57–288.82 eV for C=O. Based on these, the chemical formulation of fullereneol was defined as $\text{Na}_n^+[\text{C}_{60}\text{O}_x(\text{OH})_y]^{n-}$, where the oxidation degree of fullereneol was regulated by the alkali concentration. The ^1H NMR spectrum showed signals at δ 1.23, 2.50 and 3.34. Only the weak peak at δ 1.23 was due to hydroxyl groups of fullereneol, the rest signals were due to water and dimethyl sulfoxide (DMSO). Enhanced ^{13}C NMR signals were observed at δ 175, 137 and 75–80, which were assigned to C=C–O, C=C and C–OH. Other weak signals were found at δ 160 for O=C–OH, δ 100 for RO–RCH–OH or RO–R₁CR₂–OH and δ 54 for C atoms in epoxy structure. In conclusion, the structure of ^{13}C -fullereneol was explored to reach the formula of $\text{Na}_n^+[\text{C}_{60}\text{O}_x(\text{OH})_y]^{n-}$ and the exact numbers depended on the reaction parameters during the hydroxylation. ^{13}C isotope labeling largely enhanced the ^{13}C -NMR signals and revealed the intact fullerene cage during the hydroxylation according to the TOF-MS. The complicated surface functional groups were reflected by IR, XPS and NMR, where multiple forms were identified as hemiacetal/hemiketal groups, epoxy groups, carboxylic ester, carbonyl groups, and so on. The results would definitely benefit the ongoing exploration of fullereneol bio-effects/bioapplications and structure-activity relationship. The ^{13}C labeled fullerene and fullereneol could be used for the quantification of carbon nanomaterials in biological systems.

fullereneol, stable isotope ^{13}C labeling, ^{13}C -nuclear magnetic resonance spectrum, structural analysis

doi: 10.1360/N972017-00178